## GEØabrics<sup>®</sup>

## **RK1 Standard Trackbed Geotextile**

EDS029-2020-02-04

```
1. Description
            Robust needlepunched nonwoven geotextile manufactured from 100% virgin
            polypropylene high tenacity fibres, engineered to provide high puncture resistance
            and high extension at break.
```

- 2. Applications RK1 is Geofabrics' standard separation and filtration geotextile for use below ballast with a new sand blanket or where there is an existing good quality formation with a small percentage of coarse particles, i.e. less than 10% by weight <14mm.
- 3. Features

b)

- With a maximum width of 6m, RK1 is specified by engineers due to its robustness and its proven ability to function in the most demanding conditions, especially important under dynamic loading beneath track ballast.
- Extensive testing has demonstrated RK1's class leading robustness and long service life under dynamic loading conditions. This is due to its high puncture resistance, high elongation at break, excellent filtration characteristics at all strains and high UV and abrasion resistance.



Test Standard	Unit	Mean Values
EN ISO 12226	kN	3.3
EN 130 12230	mm	65
EN ISO 10210	kN/m	22
EN 130 10319	%	80
EN ISO 13433	mm	13
EN ISO 12956	μm	60
EN 100 11059	l/(m²⋅s)	50
EN 130 1 1036	m/s	3 · 10 <sup>-3</sup>
EN ISO 9863-1	mm	3
		1% active carbon black
		Black
		100% virgin polypropylene
	Test Standard   EN ISO 12236   EN ISO 10319   EN ISO 13433   EN ISO 12956   EN ISO 11058   EN ISO 9863-1	Test Standard Unit   EN ISO 12236 kN mm kN/m   EN ISO 10319 %   EN ISO 13433 mm   EN ISO 12956 µm I/(m²·s) m/s   EN ISO 11058 l/(m²·s) m/s

Mean values indicate the arithmetic mean derived from the samples taken for any one test as defined in the standard - usually an overall mean of five samples a)

Mean values are subject to tolerances based on 95% confidence limits as published on the product CE declaration of performance. Nominal thickness values indicate an average manufacturing norm and not a controlled performance parameter.

MD: Machine Direction (longitudinal to the roll). c)

CMD: Cross Machine Direction (across the roll). d) Tensile testing is performed using extensor

e) rensile testing is performed using extensioneters.		
	Test Standard	Values
7. Durability – Composite		
Weathering 50 MJ/m <sup>2</sup> (1 month)	EN ISO 12224	>90% Retained Strength
Microbiological resistance	EN ISO 12225	No loss in strength
Resistance to acids & alkalis	EN ISO 14030	No loss in strength
Oxidation at 112 days (100 years)	EN ISO 13438	>90% Retained Strength

8. Needle Detection	During manufacture, the protection geotextile passes close to three sets of magnets which remove metal particles up to 12g and >2mm. Just before the roll up, the geotextile passes through an electronic metal detection field. Audio and visual alarms indicate if metal particles are detected. Rolls are sent to stock if they pass through the field without an alarm event, otherwise the operator inspects the suspect area, locates any metal particles and removes them. If unsuccessful, or if any doubt remains as to the presence of metal particles, then the roll goes to the re-inspection facility.
---------------------	---

- 9. Testing All materials are tested every 6000m<sup>2</sup> in an UKAS accredited ISO 17025 laboratory to all mechanical properties prior to release.
- 10. Storage The geotextiles are supplied in packaging designed to protect the product from damage during handling, storage and degradation as a result of UV exposure. The product should be kept in appropriate packaging until such time that it is required for installation. The product is clearly and indelibly marked with its name along the edge of the roll at regular intervals, no greater than 5m. The packaging is clearly labelled to identify the product supplied, in accordance with EN ISO 10320: Geotextile and Geotextile related products - Identification on site. Use slings where provided. Product weights are given on roll tickets. Use equipment appropriate to weight and dimensions. Store and handle in accordance with good occupational health and safety practice.

	Unit	Values
11. Dimensions		
Standard roll length	m	50
Standard roll width	m	4
Approximate roll weight	Kg	80

Geofabrics Limited, Skelton Grange Road, Stourton, Leeds LS10 1RZ, United Kingdom